Integrity Wood-Ultrex

	LoĒ^2-272®			LoĒ^3-366®	
	U Factor	SHGC	VLT	Energy Star	Qualifies for Tax Credit
Wood-Ultrex Awning - 3 mm glass					
Insulating LoĒ^2-272 Glass - Argon	0.29	0.30	0.51	N, NC, SC	X
Insulating LoĒ^2-272 Glass - Argon, GBG	0.29	0.27	0.46	N, NC, SC, S	X
Insulating LoĒ^2-272 Glass - Argon, SDL w/o Spacer Bar	0.29	0.27	0.46	N, NC, SC, S	X
Insulating LoĒ^3- 366 Glass - Argon	0.28	0.20	0.46	N, NC, SC, S	X
Insulating LoĒ^3- 366 Glass - Argon, GBG	0.29	0.18	0.42	N, NC, SC, S	X
Insulating LoĒ3- 366 Glass - Argon, SDL w/ Spacer Bar (SDLS)	0.28	0.18	0.42	N, NC, SC, S	X
Insulating LoĒ^3- 366 Glass - Argon, SDL w/o Spacer Bar	0.28	0.18	0.42	N, NC, SC, S	X

Wood-Ultrex Casement - 3 mm glass					
Insulating LoĒ^2-272 Glass - Argon	0.29	0.30	0.51	N, NC, SC	X
Insulating LoĒ^2-272 Glass - Argon, GBG	0.30	0.28	0.46	N, NC, SC, S	X
Insulating LoĒ^2-272 Glass - Argon, SDL w/o Spacer Bar	0.29	0.28	0.46	N, NC, SC, S	X
Insulating LoĒ^3- 366 Glass - Argon	0.29	0.20	0.46	N, NC, SC, S	X
Insulating LoĒ^3- 366 Glass - Argon, GBG	0.29	0.18	0.42	N, NC, SC, S	X
Insulating LoĒ3- 366 Glass - Argon, SDL w/ Spacer Bar (SDLS)	0.28	0.18	0.42	N, NC, SC, S	X
Insulating LoĒ^3- 366 Glass - Argon, SDL w/o Spacer Bar	0.29	0.18	0.42	N, NC, SC, S	X

Wood-Ultrex Casement Picture - 3 mm glass					
Insulating LoĒ^2-272 Glass - Argon	0.28	0.34	0.58	N, NC	
Insulating LoĒ^2-272 Glass - Argon, GBG	0.28	0.31	0.52	N, NC	
Insulating LoĒ^2-272 Glass - Argon, SDL w/o Spacer Bar	0.28	0.31	0.52	N, NC	
Insulating LoĒ^3- 366 Glass - Argon	0.27	0.23	0.53	N, NC, SC, S	X
Insulating LoĒ^3- 366 Glass - Argon, GBG	0.28	0.21	0.47	N, NC, SC, S	X
Insulating LoĒ3- 366 Glass - Argon, SDL w/ Spacer Bar (SDLS)	0.27	0.20	0.47	N, NC, SC, S	X
Insulating LoĒ^3- 366 Glass - Argon, SDL w/o Spacer Bar	0.27	0.21	0.47	N, NC, SC, S	X

Wood-Ultrex Double Hung - 3 mm glass					
Insulating LoĒ^2-272 Glass - Argon	0.29	0.32	0.54	N, NC	
Insulating LoĒ^2-272 Glass - Argon, GBG	0.29	0.28	0.48	N, NC, SC, S	X
Insulating LoĒ^2-272 Glass - Argon, SDL w/o Spacer Bar	0.29	0.28	0.48	N, NC, SC, S	X
Insulating LoĒ^3- 366 Glass - Argon	0.28	0.21	0.49	N, NC, SC, S	X
Insulating LoĒ^3- 366 Glass - Argon, GBG	0.28	0.19	0.43	N, NC, SC, S	X
Insulating LoĒ^3- 366 Glass - Argon, SDL w/ Spacer Bar (SDLS)	0.29	0.19	0.43	N, NC, SC, S	X
Insulating LoĒ^3- 366 Glass - Argon, SDL w/o Spacer Bar	0.28	0.19	0.43	N, NC, SC, S	X

Integrity Wood-Ultrex

	LoĒ^2-272®			LoĒ^3-366®	
	U Factor	SHGC	VLT	Energy Star	Qualifies for Tax Credit
Wood-Ultrex Double Hung Picture/Transom - 3 mm glass					
Insulating LoĒ^2-272 Glass - Argon	0.28	0.33	0.57	N, NC	
Insulating LoĒ^2-272 Glass - Argon, GBG	0.29	0.30	0.51	N, NC, SC	X
Insulating LoĒ^2-272 Glass - Argon, SDL w/o Spacer Bar	0.28	0.30	0.51	N, NC, SC	X
Insulating LoĒ^3- 366 Glass - Argon	0.27	0.22	0.51	N, NC, SC, S	X
Insulating LoĒ^3- 366 Glass - Argon, GBG	0.28	0.20	0.45	N, NC, SC, S	X
Insulating LoĒ^3- 366 Glass - Argon, SDL w/ Spacer Bar (SDLS)	0.27	0.20	0.45	N, NC, SC, S	X
Insulating LoĒ^3- 366 Glass - Argon, SDL w/o Spacer Bar	0.27	0.20	0.45	N, NC, SC, S	X
Wood-Ultrex Glider - XO or OX - 3 mm glass					
Insulating LoĒ^2-272 Glass - Argon	0.30	0.31	0.54	N, NC	
Insulating LoĒ^2-272 Glass - Argon, GBG	0.30	0.28	0.48	N, NC, SC, S	X
Insulating LoĒ^2-272 Glass - Argon, SDL w/o Spacer Bar	0.30	0.28	0.48	N, NC, SC, S	X
Insulating LoĒ^3- 366 Glass - Argon	0.29	0.20	0.49	N, NC, SC, S	X
Insulating LoĒ^3- 366 Glass - Argon, GBG	0.30	0.19	0.43	N, NC, SC, S	X
Insulating LoĒ^3- 366 Glass - Argon, SDL w/ Spacer Bar (SDLS)	0.29	0.19	0.43	N, NC, SC, S	X
Insulating LoĒ^3- 366 Glass - Argon, SDL w/o Spacer Bar	0.29	0.19	0.43	N, NC, SC, S	X
Wood-Ultrex Casement Round Top - 3 mm glass					
Insulating LoĒ^2-272 Glass - Argon	0.28	0.36	0.62	N, NC	
Insulating LoĒ^2-272 Glass - Argon, GBG	0.29	0.33	0.56	N, NC	
Insulating LoĒ^2-272 Glass - Argon, SDL w/o Spacer Bar	0.28	0.33	0.56	N, NC	
Insulating LoĒ^3- 366 Glass - Argon	0.27	0.24	0.56	N, NC, SC, S	X
Insulating LoĒ^3- 366 Glass - Argon, GBG	0.28	0.22	0.50	N, NC, SC, S	X
Insulating LoĒ^3- 366 Glass - Argon, SDL w/ Spacer Bar (SDLS)	0.27	0.22	0.50	N, NC, SC, S	X
Insulating LoĒ^3- 366 Glass - Argon, SDL w/o Spacer Bar	0.27	0.22	0.50	N, NC, SC, S	X
Wood-Ultrex Casement Round Tops by Marvin - 3 mm glass					
Insulating LoĒ^2-272 Glass - Argon	0.29	0.37	0.64	N, NC	
Insulating LoĒ^2-272 Glass - Argon, GBG	0.29	0.33	0.57	N, NC	
Insulating LoĒ^2-272 Glass - Argon, SDL w/o Spacer Bar	0.29	0.33	0.57	N, NC	
Insulating LoĒ^3- 366 Glass - Argon	0.28	0.24	0.58	N, NC, SC, S	X
Insulating LoĒ^3- 366 Glass - Argon, GBG	0.28	0.22	0.52	N, NC, SC, S	X
Insulating LoĒ^3- 366 Glass - Argon, SDL w/ Spacer Bar (SDLS)	0.29	0.22	0.52	N, NC, SC, S	X
Insulating LoĒ^3- 366 Glass - Argon, SDL w/o Spacer Bar	0.28	0.22	0.52	N, NC, SC, S	X

Integrity Wood-Ultrex

	LoĒ^2-272®			LoĒ^3-366®	
	U Factor	SHGC	VLT	Energy Star	Qualifies for Tax Credit
Wood-Ultrex Double Hung Round Top - 3 mm glass					
Insulating LoĒ^2-272 Glass - Argon	0.28	0.37	0.64	N, NC	
Insulating LoĒ^2-272 Glass - Argon, GBG	0.29	0.33	0.57	N, NC	
Insulating LoĒ^2-272 Glass - Argon, SDL w/o Spacer Bar	0.28	0.33	0.57	N, NC	
Insulating LoĒ^3- 366 Glass - Argon	0.27	0.24	0.57	N, NC, SC, S	X
Insulating LoĒ^3- 366 Glass - Argon, GBG	0.28	0.22	0.51	N, NC, SC, S	X
Insulating LoĒ^3- 366 Glass - Argon, SDL w/ Spacer Bar (SDLS)	0.27	0.22	0.51	N, NC, SC, S	X
Insulating LoĒ^3- 366 Glass - Argon, SDL w/o Spacer Bar	0.27	0.22	0.51	N, NC, SC, S	X
Wood-Ultrex Double Hung Round Tops by Marvin - 3 mm glass					
Insulating LoĒ^2-272 Glass - Argon	0.29	0.36	0.61	N, NC	
Insulating LoĒ^2-272 Glass - Argon, GBG	0.29	0.32	0.55	N, NC	
Insulating LoĒ^2-272 Glass - Argon, SDL w/o Spacer Bar	0.29	0.32	0.55	N, NC	
Insulating LoĒ^3- 366 Glass - Argon	0.28	0.24	0.55	N, NC, SC, S	X
Insulating LoĒ^3- 366 Glass - Argon, GBG	0.28	0.21	0.50	N, NC, SC, S	X
Insulating LoĒ^3- 366 Glass - Argon, SDL w/ Spacer Bar (SDLS)	0.29	0.21	0.50	N, NC, SC, S	X
Insulating LoĒ^3- 366 Glass - Argon, SDL w/o Spacer Bar	0.28	0.21	0.50	N, NC, SC, S	X
Wood-Ultrex Direct Glaze Polygon - 3 mm glass					
Insulating LoĒ^2-272 Glass - Argon	0.27	0.35	0.61	N, NC	
Insulating LoĒ^2-272 Glass - Argon, GBG	0.28	0.32	0.54	N, NC	
Insulating LoĒ^2-272 Glass - Argon, SDL w/o Spacer Bar	0.27	0.32	0.54	N, NC	
Insulating LoĒ^3- 366 Glass - Argon	0.27	0.23	0.54	N, NC, SC, S	X
Insulating LoĒ^3- 366 Glass - Argon, GBG	0.28	0.21	0.49	N, NC, SC, S	X
Insulating LoĒ^3- 366 Glass - Argon, SDL w/ Spacer Bar (SDLS)	0.27	0.21	0.49	N, NC, SC, S	X
Insulating LoĒ^3- 366 Glass - Argon, SDL w/o Spacer Bar	0.27	0.21	0.49	N, NC, SC, S	X
Wood-Ultrex Sliding Patio Door - 3 mm glass					
Insulating LoĒ^2-272 Glass - Argon	0.29	0.34	0.58		
Insulating LoĒ^2-272 Glass - Argon, GBG	0.29	0.30	0.51	N, NC, SC, S	X
Insulating LoĒ^2-272 Glass - Argon, SDL w/o Spacer Bar	0.29	0.30	0.51	N, NC, SC, S	X
Insulating LoĒ^3- 366 Glass - Argon	0.28	0.22	0.52	N, NC, SC, S	X
Insulating LoĒ^3- 366 Glass - Argon, GBG	0.28	0.20	0.46	N, NC, SC, S	X
Insulating LoĒ^3- 366 Glass - Argon, SDL w/ Spacer Bar (SDLS)	0.29	0.20	0.46	N, NC, SC, S	X
Insulating LoĒ^3- 366 Glass - Argon, SDL w/o Spacer Bar	0.28	0.20	0.46	N, NC, SC, S	X

Integrity Wood-Ultrex

	LoĒ^2-272®			LoĒ^3-366®	
	U Factor	SHGC	VLT	Energy Star	Qualifies for Tax Credit
Wood-Ultrex Sliding French Door - 3 mm glass					
Insulating LoĒ^2-272 Glass - Argon	0.30	0.29	0.50	N, NC, SC, S	X
Insulating LoĒ^2-272 Glass - Argon, GBG	0.30	0.26	0.43	N, NC, SC, S	X
Insulating LoĒ^2-272 Glass - Argon, SDL w/o Spacer Bar	0.30	0.26	0.43	N, NC, SC, S	X
Insulating LoĒ^3- 366 Glass - Argon	0.30	0.19	0.45	N, NC, SC, S	X
Insulating LoĒ^3- 366 Glass - Argon, GBG	0.30	0.17	0.39	N, NC, SC, S	X
Insulating LoĒ^3- 366 Glass - Argon, SDL w/ Spacer Bar (SDLS)	0.31	0.17	0.39	N, NC, SC, S	
Insulating LoĒ^3- 366 Glass - Argon, SDL w/o Spacer Bar	0.30	0.17	0.39	N, NC, SC, S	X

Wood-Ultrex Inswing French Door - 3 mm glass					
Insulating LoĒ^2-272 Glass - Argon	0.30	0.27	0.47	N, NC, SC, S	X
Insulating LoĒ^2-272 Glass - Argon, GBG	0.30	0.24	0.40	N, NC, SC, S	X
Insulating LoĒ^2-272 Glass - Argon, SDL w/o Spacer Bar	0.30	0.24	0.40	N, NC, SC, S	X
Insulating LoĒ^3- 366 Glass - Argon	0.30	0.18	0.42	N, NC, SC, S	X
Insulating LoĒ^3- 366 Glass - Argon, GBG	0.30	0.16	0.36	N, NC, SC, S	X
Insulating LoĒ^3- 366 Glass - Argon, SDL w/ Spacer Bar (SDLS)	0.31	0.16	0.36	N, NC, SC, S	
Insulating LoĒ^3- 366 Glass - Argon, SDL w/o Spacer Bar	0.30	0.16	0.36	N, NC, SC, S	X

Wood-Ultrex Outswing French Door - 3 mm glass					
Insulating LoĒ^2-272 Glass - Argon	0.31	0.28	0.47	N, NC, SC, S	
Insulating LoĒ^2-272 Glass - Argon, GBG	0.31	0.24	0.40	N, NC, SC, S	
Insulating LoĒ^2-272 Glass - Argon, SDL w/o Spacer Bar	0.31	0.24	0.40	N, NC, SC, S	
Insulating LoĒ^3- 366 Glass - Argon	0.30	0.19	0.42	N, NC, SC, S	X
Insulating LoĒ^3- 366 Glass - Argon, GBG	0.30	0.17	0.36	N, NC, SC, S	X